



**DETAILED ESTIMATE
FOR SUNDRAPE VERTICAL BLINDS
LOUVRE FABRICS**

product: Contour I 5800
 quality: see sundrape® drapery designs
 louvre width:..... mm
 consisting of:

material:
 PET, präcision blocking foil
 Quality 5800 2R screen stamping
 physical characteristics:
 weight of material: abt. 110 g/qm
 non-fading according to DIN EN 105-B01: 8

Physikalische Eigenschaften	5800	5807	5808	5809
transmission factor:	2,5 %	17,0 %	2,3 %	2,5 %
UV- transmission factor:	1 %	1 %	1 %	1 %
reflexion in %:	80	64	79	80
absorption in %:	17,5	19	18,7	17,5
transmission in %:	2,5	17	2,3	2,5
total energy transmission degree gt:	0,29	0,38	0,30	0,29
reduction factor Fc:	0,41	0,52	0,42	0,41
openess factor	2R	10R	2R	2R

utilization:

In any area of domestic and project buildings, recommended for computer work places according to ISO 9241-6, computer work places decree, to EU regulation (90/270/EWG) and work station regulations (§ 7 und § 9) as well as for humid rooms.