

DETAILED ESTIMATE
FOR SUNDRAPE PANEL CURTAIN
LOUVRE FABRICS



product: Interloon® Screen I 430
quality: see sundrape® drapery designs
drapery width: 2400 mm
consisting of:

material:
100% polyester
PVC- and halogen-free coating
no lateral hem necessary

physical characteristics:

weight of material: abt. 205 g/qm
non-fading according to DIN EN 105-B01: 5
semi transparent

	430	431	432	433
reflexion in %:	54	53	45	36
absorption in %:	2	8	17	35
transmission in %:	44	39	38	29
total energy transmission degree gt:	0,45	0,45	0,49	0,49
reduction factor Fc:	0,62	0,63	0,68	0,68

	434	435	436	437	438
reflexion in %:	7	25	8	26	5
absorption in %:	83	55	83	57	88
transmission in %:	10	20	9	17	7
total energy transmission degree gt:	0,53	0,51	0,52	0,48	0,64
reduction factor Fc:	0,74	0,70	0,73	0,67	0,89

behaviour in fire:
flame resistant according to (DE) DIN 4102 B1

Öko-Tex Standard 100

moisture proof
moisty wipping

utilization:
In any area of domestic and project buildings.