

DETAILED ESTIMATE  
FOR SUNDRAPE PANEL CURTAIN  
LOUVRE FABRICS



product: Interloon® Trevira® CS 8001  
quality: see sundrape® drapery designs  
drapery width: 1800 mm  
consisting of:

material:  
100% polyester, Trevira CS  
no lateral hem necessary

physical characteristics:  
weight of material: abt. 270 g/qm  
non-fading according to DIN EN 105-B01: 5-7  
AMP antimicrobiological protection  
use in hygienic sensitive areas recommended  
PVC- and halogen-free coating

	8034	8001	8033	8005	8006
reflexion in %	64	64	58	41	41
absorption in %	2	2	11	37	37
transmission in %	34	34	31	22	22
total energy transmission degree gt:	0,39	0,39	0,41	0,49	0,49
reduction factor Fc:	0,54	0,54	0,57	0,67	0,67

	8007	8014	8026	8025
reflexion in %	58	58	41	48
absorption in %	11	11	37	25
transmission in %	31	31	22	27
total energy transmission degree gt:	0,41	0,41	0,49	0,46
reduction factor Fc:	0,57	0,57	0,67	0,63

behaviour in fire:  
flame resistant according to (DE) DIN 4102 B1

Trevira CS trade mark release: 061673

utilization:  
In any area of domestic and project buildings.